

FEATURES

Nippon Paint Dan Trans Sealer is a chlorinated rubber resin primer. It specially formulated to use before elastomeric textured paint to provide excellent adhesion, excellent alkali and efflorescence resistance. It can be used on concrete, plaster, both interior and exterior walls.

- Good adhesion and coverage
- Resistance against fungus and algae
- Can be used for both new construction and renovation
- Good alkali and efflorescence resistance

PRODUCT INFORMATION

Paint type	Chlorinated Resin
Product type	Exterior and Interior
Film appearance	Gloss
Colour	Clear
Recommended substrate	Masonry, plastering, concrete, brick, fibre cement board, etc.
Pack size	16 kg

TECHNICAL INFORMATION

Theoretical coverage	0.13 - 0.14	kg per m ² per coat
	7 - 8	m ² per kg per coat
	114 - 123	m ² per pail
	(Actual coverage is dependent on substrate condition and application method)	
No. of coat	1	Coat
Solid by volume	38 - 42	%
Solid by weight	54 - 58	%
Touch dry (25-30°C)	10	minutes
Recoat dry (25-30°C)	more than 1	hours
Full cure (25-30°C)	7	days

REFERENCE STANDARD

-

APPLICATION

Application Method	Brush, Roller or Spray
Diluted by	-
Dilution (%)	No thinning is required. Should stir the paint before use.

SURFACE PREPARATION

Old Surface	Remove all loose, defective paint or powdery residues, loose chalk, dust, fungus, algae and foreign matter. (avoid wire brush) Repair cracks, uneven surfaces with Nippon Paint Vinilex Wall Putty. Treat any areas affected by fungus growth by scrubbing and allowing the surface to dry completely before painting then apply with Nippon Paint Vinilex Bio Wash 1 coat and leave it until dry.
New Surface	Ensure that the surface is clean and dry it must be free from dirt, greases and other foreign matters. Allow all surfaces to dry completely prior to painting. (At least 28 days) Avoid painting

when the moisture content and alkalinity of the walls are still high. (Recommended painting specification requires the moisture content of the walls to be below 14% measured by protimeter, below 6% by Kett model HI-520 and alkalinity of the walls to be below pH 8.) Repair cracks, uneven surfaces with Nippon Paint Vinilex Wall Putty.

PAINT SYSTEM

New Wall Primer	Nippon Paint Dan Trans Sealer 1 coat
Top Coat	Nippon Paint Dan Uni 1 coat

HANDLING AND STORAGE

Storage condition	The product must be stored in a dry, well-ventilated space and keep the container tightly closed. When transporting paint, the product should separately from others. Not recommended to place the product outdoor or exposed to the sun directly and must separately be stored between enamel paint and thinner, which is a flammable substance.
Precipitation	Place the product for a long time may lead the pigment to precipitate at the bottom of the container and can deteriorate over time when not stir product to a homogeneous by using suitable tools, such as an electric drill, air drill, or a stirrer. Therefore, should stir the product to the homogeneous phase before use. If not, the product will cause paint problems e.g. low hiding power or non-equal color shade.
Shelf life	1 year at 30 - 35 °C

SAFETY PRECAUTIONS

Precautionary notices are displayed on the container. Use product under well-ventilated area. During use, the product must keep away from the source of ignition and no smoking. Avoiding skin contact or inhale product. In case of contact with the eye, rinse with plenty of water immediately and seek medical advice. Remove splashes from the skin by using soap or water. For others information in terms of health and safety hazards for use of this product, please observe the Safety Data Sheet.

DISCLAIMER

The above information is given to the best of our knowledge based on laboratory tests and practical experience. However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself. We reserve the right to alter the given without prior notice.

NOTE

The data are average values for reference only. However, the actual value depends on environmental conditions.